



UNITEM Sfx-0149 extruded thermoplastic shapes provide users with the strength, temperature resistance and dimensional stability inherent in polyetherimide based resins as well as enhanced stiffness provided by the addition of a metallic filler.

UNITEM Sfx-0149 extruded shapes offer low extractables for applications requiring FDA compliance and are offered in a broad range of rod, plate and tube configurations by special order.

Typical Physical Properties

Property	Test Method	Unit	Nominal Value*
Mechanical			
Specific Gravity	ASTM D792	---	1.49
Tensile Strength	ASTM D638	psi	13,000
Tensile Elong. @ Break	ASTM D638	%	3.0
Tensile Modulus	ASTM D638	psi	525,000
Flexural Strength	ASTM D790	psi	25,000
Flexural Modulus	ASTM D790	psi	560,000
Izod Impact (notched)	ASTM D256	ft.-lb./in.	1.0
Rockwell Hardness	ASTM D785	D Scale	109
Thermal			
Maximum C.U.T.	NITM	°F	418
HDT @ 264 psi	ASTM D648	°F	388
Coef. Of Thermal Expansion	ASTM D696	in./in./ °F x 10 ⁻⁵	3.0
Flammability	UL 94	3.0mm	V-0
Miscellaneous			
Water Absorption (24 hrs.)	ASTM D792	%	0.25
Color	--	--	Amber/Gray

Nytef Plastics, Ltd. believes that the information presented here is the best available at the time of publication. This information is intended only as a guideline and Nytef Plastics, Ltd. makes no guarantee as to its accuracy or completeness and will not assume any obligation or liability whatsoever for the use of this information. *Nominal Property Values are based on tests of injection molded plaques; properties of extruded shapes may differ from values shown.



NYTEFPLASTICS
800-646-9833
 www.nytec.com
 sales@nytec.com