



# POLYMER INDUSTRIES

## PET

### TYPICAL PROPERTIES

Property	Test Method	Units	PET
<b>Mechanical</b>			
Specific Gravity	ASTM-D792	---	1.34
Tensile Strength	ASTM-D638	psi	12,200
Tensile Elongation	ASTM-D638	%	25
Tensile Modulus	ASTM-D638	psi	470,000
Flexural Strength	ASTM-D790	psi	17,500
Flexural Modulus	ASTM-D790	psi	490,000
Izod Notched Impact	ASTM-D256	ft.- lb./in.	0.6
Rockwell Hardness	ASTM-D785	R scale	R125
<b>Thermal</b>			
Coef. Of Linear Thermal Expansion	ASTM-D696	in./in./°F	3.6x10 <sup>-5</sup>
Max Continuous Temp.	Internal Std.	°F	230
Heat Defl. Temp. @ 264 psi	ASTM-D648	°F	190
Melting Point	ASTM-D3418	°F	491
<b>Electrical</b>			
Dielectric Strength-Short Term	ASTM-D149	volts/mil	450
Dielectric Constant @ 60 Hz	ASTM-D150	---	3.4
Dissipation Factor @ 60 Hz	ASTM-D150	---	0.002
Volume Resistivity	ASTM-D257	ohm-cm	>10 <sup>14</sup>
<b>Miscellaneous</b>			
Water Absorption/24 hours	ASTM-D570	% weight	0.01
Water Absorption @ Saturation	ASTM-D570	% weight	0.9
Flammability	UL-94	---	HB
<b>Agency Compliance</b>			
FDA	---	---	Yes
USDA	---	---	Yes
3-A Dairy Standards	---	---	Yes

MECHETEC® Is a registered trademark of Polymer Industries

